

## Ethyl Series Instant Bonders

## Technical Data Sheet

**GENERAL INFORMATION:** SAF-T-LOK cyanoacrylate adhesives are a specialized series of single component, solvent free liquids that are individually formulated for instant bonding of mated metals, plastic or rubber parts and assemblies.

**Instant Bonders** adhesives cure at room temperature without pressure to provide exceedingly high bond strengths. Cure is catalyzed by weak alkaline materials including trace amount of moisture on the surface of parts to be bonded. Shrinkage is negligible because **Instant Bonders** adhesives contain 100% reactive materials. Solvent resistance is very good.

**PRODUCT DESCRIPTION:** SAF-T-LOK Ethyl Series Instant Bonders are offered in various grades which were developed to provide a range of viscosities for specific bonding requirements with engineered substrates. This ethyl series of cyanoacrylate products satisfies most application requirements. The range of viscosity permits selection of a product thickness to accommodate the bonding gap of specified assemblies.

	IB 5	IB 20	IB 45	IB 100	IB 300	IB 600	IB 1500	IB 2500
Viscosity (cps)	5	20	45	100	300	600	1500	2500
Gap Fill (in)	.002	.002	.003	.004	.005	.006	.010	.015

### PRODUCT CHARACTERISTICS:

Base	Ethyl Cyanoacrylate
Color	Colorless/Transparent
Solid Content	100%
Solvent Content	Zero
Specific Gravity	1.06
Refractive Index	1.45 (similar to glass)
Flash Point (SETA)	185°F

### Resistance Qualities:

- (1) Temperature - Varies with substrate and exposure though in general optimum bonding performance within range of -114°F to +180°F.
- (2) Water - Unaffected for several weeks, after which poorly designed joint strength may decrease as much as 25% in shear values.
- (3) Oils - good resistance to motor oils.
- (4) Acids/Alkali - Generally good for dilute solutions, though prolonged immersion can decrease adhesive strength.

**IMPORTANT NOTICE:** All statements and technical data contained herein are based on tests we believe to be reliable, but the accuracy of completeness thereof is not guaranteed. It is recommended that the buyer test this product to determine its suitability for his application before use. SAF-T-LOK International Corporation is not responsible for loss, claim or damages resulting from use of its products.