

PRODUCT DESCRIPTION:

SAF-T-LOK T72 is a high strength locking and sealing grade, developed for key fits, splines, and similar applications, as well as removable applications. **SAF-T-LOK T72** is a thixotropic formulation to reduce run-off, or reduce migration of product prior to assembly. It was also designed to provide predictable assembly lubricity and results in the same torque tension relationship that would result from use of as received fasteners. This product satisfies many application requirements where a high strength is required. Selection of this product assures fluid sealing of parts as well as the most reliable high threadlocking strength possible.

GENERAL INFORMATION:

SAF-T-LOK anaerobic adhesive/sealants are a specialized series of single component, solvent free compounds that are individually formulated for locking, sealing, retaining and bonding metal parts and assemblies.

Stable in the presence of air, these products cure when placed between two mating parts where metal is present and oxygen is excluded. They form a resilient, vibration proof, polymer shim between the parts. **SAF-T-LOK** products provide the user with additional performance characteristics, including not only fluid sealing, but resistance to corrosion and galvanic attack of the mated parts, as well as solvent resistance. Furthermore, after curing **SAF-T-LOK T72** allows parts to be disassembled with normal tools, if desired.

PHYSICAL PROPERTIES:

Color:	Red
Specific Gravity:	1.09 gm/cc
Viscosity: (lv, spindle 3, speed 12)	5000 to 8000 cps
Temperature Range:	-65°F to 400°F (450°F intermittent)
Storage Stability:	+12 months at <75°F

PERFORMANCE CHARACTERISTICS:

Locking Torque Breakaway: Prevailing:	150 - 350 in lbs 150 - 500 in lbs
Gap Filling:	.001-.010 in.
Full Cure:	24 hours

NOTE: This product is not recommended for use with pure oxygen systems.

IMPORTANT NOTICE: All statements and technical data contained herein are based on tests we believe to be reliable, but the accuracy of completeness thereof is not guaranteed. It is recommended that the buyer test this product to determine its suitability for his application before use. **SAF-T-LOK International Corporation** is not responsible for loss, claim or damages resulting from use of its products.

TECHNICAL SUPPORT

Our technical support team stands ready to assist you with your technical questions regarding your SAF-T-LOK products. On-Site support when necessary within 24 hours.

PART NUMBERS

27221	10ml
27231	50ml
27241	250ml
27243	1 liter

TURNKEY SOLUTIONS

As an ISO 9001:2015 certified company, SAF-T-LOK can design or refine products to fit your company's specific needs and requirements.

For more information on any of our products or services please visit us on the Web at:

www.saflok.com